



P: 1.800.999.1700 | F: 610.459.1084 | info@westlakeplastics.com | 490 West Lenni Road, Lenni, PA 19052 U.S.A.

Absylux®



Absylux® ABS, Acrylonitrile Butadiene Styrene, is a thermoplastic terpolymer composed of acrylonitrile, butadiene, and styrene. Absylux® ABS has good chemical and stress-cracking resistance to inorganic salt solutions, alkalis, most mineral acids, and some mineral, vegetable, and animal-based oils. Absylux® ABS is an ideal material for structural applications when impact resistance, strength, stiffness, and moderate heat resistance are required. Absylux ABS is made from resin that is suitable for use in certain food contact applications. Please contact your local Westlake Plastics representative for compliance standards that the resin conforms to and for regulatory declarations. Westlake's unique compression molding and stress relieving processes deliver thick gauge sheets with exceptional dimensional stability allowing them to be machined in complex shapes with tight tolerances. In thin sheet form it is easy to thermoform. Absylux® ABS is also one of the few non-metallic materials which can be readily electro-plated and is easy to paint and glue.

INDUSTRY



Engineering

COLORS AVAILABLE



Black Natural White

ATTRIBUTES



Food Contact



Impact Resistance



Dimensional Stability



SHAPES

Compression Sheet



Extruded Sheet



Extruded Film



Extruded Rod





P: 1.800.999.1700 | F: 610.459.1084 | info@westlakeplastics.com | 490 West Lenni Road, Lenni, PA 19052 U.S.A.

Absylux®

TYPICAL PROPERTIES

PROPERTY	TEST STANDARD	ENGLISH UNITS	METRIC UNITS
Mechanical			
Flexural Modulus	D790	313 kpsi	2,160 MPa
Flexural Strength - Yield	D790	9.6 kpsi	66 MPa
Izod Impact Resistance, Notched	D256	8.09 ft-lb/in	432 J/m
Tensile Elongation @ Break	D638	32 %	32 %
Tensile Elongation @ Yield	D638	3.1 %	3.1 %
Tensile Modulus	D638	301 kpsi	2,080 MPa
Tensile Strength @ Break	D638	4.4 kpsi	30 MPa
Tensile Strength @ Yield	D638	5.7 kpsi	30 MPa
Thermal			
HDT @ 264 psi	D648	168.8 °F	76 °C
HDT @ 64 psi	D648	195.8 °F	91 °C
Physical			
Specific Gravity	D792	1.03	1.03

*Data above is based on testing of injection molded test specimens



P: 1.800.999.1700 | F: 610.459.1084 | info@westlakeplastics.com | 490 West Lenni Road, Lenni, PA 19052 U.S.A.

Absylux®

PRODUCT SHAPES & DIMENSIONS

Rods: 48"L (122cm)

2.25" (57.15mm)	2.5" (63.5mm)	2.75" (69.85mm)	3" (76.2mm)	3.25" (82.55mm)	3.5" (88.9mm)
3.75" (95.25mm)	4" (101.6mm)				

Rods: 96"L (244cm)

0.5" (12.7mm)	0.75" (19.05mm)	1" (25.4mm)	1.25" (31.75mm)	1.5" (38.1mm)	1.75" (44.45mm)
2.0" (50.8mm)					

Compression Sheets: 24"W x 48"L (61cm x 122cm)

0.25" (6.35mm)	0.375" (9.53mm)	0.5" (12.7mm)	0.75" (19.05mm)	1" (25.4mm)	1.25" (31.75mm)
1.50" (38.1mm)	1.75" (44.45mm)	2" (50.8mm)	2.25" (57.15mm)	2.50" (63.5mm)	2.75" (69.85mm)
3" (76.2mm)	3.25" (82.55mm)	3.50" (88.9mm)	3.75" (95.25mm)	4" (101.6mm)	4.25" (107.95mm)
4.50" (114.3mm)	4.75" (120.65mm)	5" (127mm)	5.25" (133.35mm)	5.50" (139.7mm)	5.75" (146.05mm)
6" (152.4mm)					

Compression Sheets: 48"W x 96"L (122cm x 244cm)

0.25" (6.35mm)	0.375" (9.53mm)	0.5" (12.7mm)	0.75" (19.05mm)	1" (25.4mm)	1.25" (31.75mm)
1.50" (38.1mm)	1.75" (44.45mm)	2" (50.8mm)	2.25" (57.15mm)	2.50" (63.5mm)	2.75" (69.85mm)
3" (76.2mm)	3.25" (82.55mm)	3.50" (88.9mm)	3.75" (95.25mm)	4" (101.6mm)	4.25" (107.95mm)
4.50" (114.3mm)	4.75" (120.65mm)	5" (127mm)	5.25" (133.35mm)	5.50" (139.7mm)	5.75" (146.05mm)
6" (152.4mm)					



P: 1.800.999.1700 | F: 610.459.1084 | info@westlakeplastics.com | 490 West Lenni Road, Lenni, PA 19052 U.S.A.

Absylux®

Compression Sheets: 48"W x 120"L (122cm x 305cm)

0.25" (6.35mm)	0.375" (9.53mm)	0.5" (12.7mm)	0.75" (19.05mm)	1" (25.4mm)	1.25" (31.75mm)
1.50" (38.1mm)	1.75" (44.45mm)	2" (50.8mm)	2.25" (57.15mm)	2.50" (63.5mm)	2.75" (69.85mm)
3" (76.2mm)	3.25" (82.55mm)	3.50" (88.9mm)	3.75" (95.25mm)	4" (101.6mm)	4.25" (107.95mm)
4.50" (114.3mm)	4.75" (120.65mm)	5" (127mm)	5.25" (133.35mm)	5.50" (139.7mm)	5.75" (146.05mm)
6" (152.4mm)					

Compression Sheets: 60"W x 120"L (152cm x 305cm)

0.25" (6.35mm)	0.375" (9.53mm)	0.5" (12.7mm)	0.75" (19.05mm)	1" (25.4mm)	1.25" (31.75mm)
1.50" (38.1mm)	1.75" (44.45mm)	2" (50.8mm)	2.25" (57.15mm)	2.50" (63.5mm)	2.75" (69.85mm)
3" (76.2mm)	3.25" (82.55mm)	3.50" (88.9mm)	3.75" (95.25mm)	4" (101.6mm)	4.25" (107.95mm)
4.50" (114.3mm)	4.75" (120.65mm)	5" (127mm)	5.25" (133.35mm)	5.50" (139.7mm)	5.75" (146.05mm)
6" (152.4mm)					

Extruded Sheets: 48"W x 96"L (122cm x 244cm)

0.03" (0.76mm)	0.035" (0.89mm)	0.06" (1.52mm)	0.062" (1.57mm)	0.08" (2.03mm)	0.09" (2.29mm)
0.095" (2.41mm)	0.125" (3.18mm)	0.1875" (4.76mm)	0.25" (6.35mm)		

Extruded Films: 26"W (66cm)

0.01" (0.25mm)	0.02" (0.51mm)
----------------	----------------

LAST REVISED: 01/30/2025

This information is offered solely for your consideration, examination and verification, and is to be construed neither as a warranty nor guarantee that the same results as those stated herein will be obtained by the use to which others may put the material. Each user of the material should make his own tests to determine the characteristics and suitability of the material for his own particular use and the use which will be made of the completed product. This publication is not to be taken as a license to operate under, or a recommendation to infringe any patents. The observance of all legal regulations and patents is the responsibility of the user. The buyer's exclusive remedy against the seller shall be for the repair or replacement of defective stock. No other remedy (including, but not limited to, incidental or consequential damages for lost profits, lost sales, injury to person or property, or other incidental or consequential loss) shall be available to the buyer.

EXCLUSION OF WARRANTIES: THERE ARE NO WARRANTIES AS TO THE MATERIAL DESCRIBED HEREIN, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR PARTICULAR PURPOSE. ANY VALUES STATED IN SELLER'S LITERATURE ARE TYPICAL PROPERTIES ONLY.