



P: 1.800.999.1700 | F: 610.459.1084 | info@westlakeplastics.com | 490 West Lenni Road, Lenni, PA 19052 U.S.A.

Norylux™ GF



Norylux™ GF is a 30% glass reinforced polyphenylene oxide. This product offers excellent dimensional stability and greater strength and stiffness at both room and elevated temperatures when compared to unfilled polyphenylene oxide.

INDUSTRY



Engineering

COLORS AVAILABLE



Grey

ATTRIBUTES

 Dielectric Properties	
 Dimensional Stability	
 Stiffness	
 Strength	

SHAPES

Compression Sheet	
-------------------	---



P: 1.800.999.1700 | F: 610.459.1084 | info@westlakeplastics.com | 490 West Lenni Road, Lenni, PA 19052 U.S.A.

Norylux™ GF

TYPICAL PROPERTIES

PROPERTY	TEST STANDARD	ENGLISH UNITS	METRIC UNITS
Mechanical			
Flexural Modulus	D790	1,013 kpsi	6,984 MPa
Flexural Strength - Yield	D790	24.9 kpsi	172 MPa
Izod Impact Resistance - Notched	D256	2.19 ft-lb/in	117 J/m
Tensile Elongation @ Break	D638	5.00 %	5.00 %
Tensile Modulus	D638	1,327 kpsi	9,150 MPa
Tensile Strength @ Break	D638	17.4 kpsi	120 MPa
Thermal			
HDT @ 264 psi	D648	275 °F	135 °C
HDT @ 64 psi	D648	284 °F	140 °C
Physical			
Moisture Absorption	D570	0.06 %	0.06 %
Specific Gravity	D792	1.31	1.31

*Data above is based on testing of injection molded test specimens



P: 1.800.999.1700 | F: 610.459.1084 | info@westlakeplastics.com | 490 West Lenni Road, Lenni, PA 19052 U.S.A.

Norylux™ GF

PRODUCT SHAPES & DIMENSIONS

Compression Sheets: 24"W x 48"L (61cm x 122cm)

0.25" (6.35mm)	0.375" (9.53mm)	0.5" (12.7mm)	0.75" (19.05mm)	1" (25.4mm)	1.5" (38.1mm)
1.75" (44.45mm)	2" (50.8mm)	2.5" (63.5mm)	3" (76.2mm)	3.5" (88.9mm)	4" (101.6mm)

Compression Sheets: 48"W x 96"L (122cm x 244cm)

1.5" (38.1mm)	3" (76.2mm)	4" (101.6mm)
---------------	-------------	--------------

Compression Sheets: 60"W x 120"L (152cm x 305cm)

1" (25.4mm)

LAST REVISED: 01/05/2024

This information is offered solely for your consideration, examination and verification, and is to be construed neither as a warranty nor guarantee that the same results as those stated herein will be obtained by the use to which others may put the material. Each user of the material should make his own tests to determine the characteristics and suitability of the material for his own particular use and the use which will be made of the completed product. This publication is not to be taken as a license to operate under, or a recommendation to infringe any patents. The observance of all legal regulations and patents is the responsibility of the user. The buyer's exclusive remedy against the seller shall be for the repair or replacement of defective stock. No other remedy (including, but not limited to, incidental or consequential damages for lost profits, lost sales, injury to person or property, or other incidental or consequential loss) shall be available to the buyer.

EXCLUSION OF WARRANTIES: THERE ARE NO WARRANTIES AS TO THE MATERIAL DESCRIBED HEREIN, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR PARTICULAR PURPOSE. ANY VALUES STATED IN SELLER'S LITERATURE ARE TYPICAL PROPERTIES ONLY.