



P: 1.800.999.1700 | F: 610.459.1084 | info@westlakeplastics.com | 490 West Lenni Road, Lenni, PA 19052 U.S.A.

Pomalux® WRX



Pomalux WRX (Wear resistant polyoxymethylene copolymer) is made from resin that is suitable for use in certain food contact applications, contact your local Westlake Plastics representative for specific regulatory declarations. Pomalux WRX is an internally lubricated acetal copolymer. It offers enhanced wear and abrasion resistance and lower coefficients of friction compared to Pomalux WR and is similarly formulated with a PFOA free permanent lubricant. Pomalux WRX offers enhanced wear and friction performance versus PTFE filled POMc without the risk of voids and inclusions that are commonly associated with compression molded and extruded PTFE filled POMc. Pomalux WRX offers high strength and stiffness and good chemical resistance making it an ideal material for load bearing and transmitting components where enhanced wear, abrasion and low friction performance are critical performance requirements such as gears, bearing, chain guides and other conveyor components. Product is available in natural (off white) and black. Other colors are available on a make to order basis.

INDUSTRY



Automotive



Engineering



Food Processing

COLORS AVAILABLE



Black



Natural

ATTRIBUTES

Strength	✓
Stiffness	✓
Chemical Resistance	✓
Wear Resistance	✓
Food Contact	✓

SHAPES

Extruded Slab	✓
Extruded Rod	✓



P: 1.800.999.1700 | F: 610.459.1084 | info@westlakeplastics.com | 490 West Lenni Road, Lenni, PA 19052 U.S.A.

Pomalux® WRX

TYPICAL PROPERTIES

PROPERTY	TEST STANDARD	ENGLISH UNITS	METRIC UNITS
Mechanical			
Tensile Strength @ Yield	ASTM D638	8 kpsi	55 MPa
Izod Impact Resistance - Notched	ASTM D256	0.76 ft-lb/in	40.5 J/M
Izod Impact Strength - Notched	ASTM D256	1.90 ft-lb/in ²	101.4 J/M
Flexural Modulus	ASTM D790	351 kpsi	2423 MPa
Moisture Absorption (24 hrs)	ISO 62	0.22 %	0.22 %
Thermal			
HDT @ 1.8 MPa (264 psi)	ASTM D648	190 °F	87.7 °C
Other			
K Factor	ASTM D3702 Modified	3.0 10-10in5min/ft-lb-hr	
COF Static	ASTM D3702 Modified	0.30	
COF Dynamic	ASTM D3702 Modified	0.26	

*Data above is based on testing of machined test specimens made from extruded bar stock



P: 1.800.999.1700 | F: 610.459.1084 | info@westlakeplastics.com | 490 West Lenni Road, Lenni, PA 19052 U.S.A.

Pomalux® WRX

PRODUCT SHAPES & DIMENSIONS

Rods: 48"L (122cm)

2.25" (57.15mm)	2.5" (63.5mm)	2.75" (69.85mm)	3.0" (76.2mm)	3.25" (82.55mm)	3.5" (88.9mm)
-----------------	---------------	-----------------	---------------	-----------------	---------------

Rods: 96"L (244cm)

2.0" (50.8mm)	2.25" (57.15mm)	2.5" (63.5mm)	2.75" (69.85mm)	3.0" (76.2mm)	3.25" (82.55mm)
3.5" (88.9mm)					

Extruded Slabs: 24"W (61cm)

0.75" (19.05mm)	1" (25.4mm)	1.5" (38.1mm)	1.75" (44.45mm)	2" (50.8mm)
-----------------	-------------	---------------	-----------------	-------------

LAST REVISED: 06/11/2025

This information is offered solely for your consideration, examination and verification, and is to be construed neither as a warranty nor guarantee that the same results as those stated herein will be obtained by the use to which others may put the material. Each user of the material should make his own tests to determine the characteristics and suitability of the material for his own particular use and the use which will be made of the completed product. This publication is not to be taken as a license to operate under, or a recommendation to infringe any patents. The observance of all legal regulations and patents is the responsibility of the user. The buyer's exclusive remedy against the seller shall be for the repair or replacement of defective stock. No other remedy (including, but not limited to, incidental or consequential damages for lost profits, lost sales, injury to person or property, or other incidental or consequential loss) shall be available to the buyer.

EXCLUSION OF WARRANTIES: THERE ARE NO WARRANTIES AS TO THE MATERIAL DESCRIBED HEREIN, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR PARTICULAR PURPOSE. ANY VALUES STATED IN SELLER'S LITERATURE ARE TYPICAL PROPERTIES ONLY.