



P: 1.800.999.1700 | F: 610.459.1084 | info@westlakeplastics.com | 490 West Lenni Road, Lenni, PA 19052 U.S.A.

Propylux™ GS



Propylux™ GS (gamma sterilizable polypropylene) extruded rods and sheets are made from FDA, USP VI compliant polypropylene resin. Its broad chemical resistance, low moisture absorption, hydrolysis resistance, and toughness make it ideal for single use medical and life science applications that will be sterilized via EtO gas, gamma or e-beam irradiation. It is formulated with a unique additive package designed to minimize the color shift and loss of mechanical properties that can typically occur with standard medical grades of polypropylene. Semi-finished shapes are stress relieved to improve dimensional stability during fabrication and end use.

INDUSTRY




COLORS AVAILABLE



Natural

ATTRIBUTES

 Impact Resistance	
 Biocompatibility	
 Chemical Resistance	

SHAPES

Extruded Sheet	
Extruded Rod	



P: 1.800.999.1700 | F: 610.459.1084 | info@westlakeplastics.com | 490 West Lenni Road, Lenni, PA 19052 U.S.A.

Propylux™ GS

TYPICAL PROPERTIES

PROPERTY	TEST STANDARD	ENGLISH UNITS	METRIC UNITS
Mechanical			
Tensile Strength @ Yield	D638	3.8 kpsi	26 MPa
Tensile Strength @ Elongation	D638	10.5%	10.5%
Flexural Modulus - Tangent	D790	138 kpsi	950 MPa
Flexural Modulus - Secant	D790	131 kpsi	900 MPa
Deflection Temperature @ 66 psi	D648	172°F	79°C
Izod Impact Resistance - Notched @ 23°C	D256	1.4 ft-lb/in	75 J/m
Gardner Impact @ 23°C	D5420	>320 in-lb	>36 J

*The data presented above is based on testing of the material using injected molded specimens.



P: 1.800.999.1700 | F: 610.459.1084 | info@westlakeplastics.com | 490 West Lenni Road, Lenni, PA 19052 U.S.A.

Propylux™ GS

PRODUCT SHAPES & DIMENSIONS

Rods: 48"L (122cm)

2.25" (57.15mm)	2.5" (63.5mm)	2.75" (69.85mm)	3.0" (76.2mm)	3.25" (82.55mm)	3.5" (88.9mm)
-----------------	---------------	-----------------	---------------	-----------------	---------------

Rods: 96"L (244cm)

0.5" (12.7mm)	0.75" (19.05mm)	1.0" (25.4mm)	1.25" (31.75mm)	1.5" (38.1mm)	1.75" (44.45mm)
2.0" (50.8mm)					

Extruded Sheets: 24"W x 48"L (61cm x 122cm)

0.5" (12.7mm)	0.75" (19.05mm)	1.0" (25.4mm)	1.25" (31.75mm)	1.5" (38.1mm)	1.75" (44.45mm)
2.0" (50.8mm)					

LAST REVISED: 01/10/2024

This information is offered solely for your consideration, examination and verification, and is to be construed neither as a warranty nor guarantee that the same results as those stated herein will be obtained by the use to which others may put the material. Each user of the material should make his own tests to determine the characteristics and suitability of the material for his own particular use and the use which will be made of the completed product. This publication is not to be taken as a license to operate under, or a recommendation to infringe any patents. The observance of all legal regulations and patents is the responsibility of the user. The buyer's exclusive remedy against the seller shall be for the repair or replacement of defective stock. No other remedy (including, but not limited to, incidental or consequential damages for lost profits, lost sales, injury to person or property, or other incidental or consequential loss) shall be available to the buyer.

EXCLUSION OF WARRANTIES: THERE ARE NO WARRANTIES AS TO THE MATERIAL DESCRIBED HEREIN, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR PARTICULAR PURPOSE. ANY VALUES STATED IN SELLER'S LITERATURE ARE TYPICAL PROPERTIES ONLY.