





P: 1.800.999.1700 | F: 610.459.1084 | info@westlakeplastics.com | 490 West Lenni Road, Lenni, PA 19052 U.S.A.

Propylux® CN-P



Propylux[™] PP CN-P (Statically conductive polypropylene) is a carbon powder-filled polypropylene offering surface resistivity in the 10e4 to 10e6 ohm/sq range and broad chemical resistance. This material is a good choice when ESD protection is needed or to minimize static discharge in flammable environments.

INDUSTRY





COLORS AVAILABLE



ATTRIBUTES



SHAPES

Compression Sheet









P: 1.800.999.1700 | F: 610.459.1084 | info@westlakeplastics.com | 490 West Lenni Road, Lenni, PA 19052 U.S.A.

Propylux® CN-P

TYPICAL PROPERTIES

| PROPERTY | TEST STANDARD | ENGLISH UNITS | METRIC UNITS |
|---------------------------------------|---------------|-------------------|------------------------------|
| Mechanical | | | |
| Tensile Strength - Yield | ASTM D638 | 3,050 psi | 21 Mpa |
| Tensile Strength - Break | ASTM D638 | 2,320 psi | 16 Mpa |
| Tensile Elongation - Yield | ASTM D638 | 8.4 % | 8.4 % |
| Tensile Elongation - Break | ASTM D638 | 48 % | 48 % |
| Tensile Modulus | ASTM D638 | 181,000 psi | 1,250 Mpa |
| Flexural Strength | ASTM D790 | 4,210 psi | 29 Mpa |
| Flexural Modulus | ASTM D790 | 170,000 psi | 1,170 Mpa |
| Izod Impact Resistance - Notched | ASTM D256 | 15 ft-lb/in | 0.8 kJ/m |
| Izod Impact Resistance - Unnotched | ASTM D4812 | no break ft-lb/in | no break kJ/m |
| Thermal | | | |
| HDT @ 264 psi | ASTM D648 | 124°F | 51°C |
| Physical | | | |
| Specific Gravity | ASTM D792 | 0.95 | 0.95 |
| Electrical | | | |
| Surface Resistivity | ASTM D257 | 10² - 106 ohm/sq | 10² - 10 ⁶ ohm/sq |

^{*}Data above is based on testing of injection molded test specimens







P: 1.800.999.1700 | F: 610.459.1084 | info@westlakeplastics.com | 490 West Lenni Road, Lenni, PA 19052 U.S.A.

Propylux® CN-P

PRODUCT SHAPES & DIMENSIONS

| Compression Sheets: | 24"W x 48 | 8"L (61cm x | 122cm) |
|---------------------|-----------|-------------|--------|
|---------------------|-----------|-------------|--------|

| | .ts. 24 W X 40 L (OICH) | X 122CIII) | | | | | | |
|--|-------------------------|----------------|-----------------|----------------|-----------------|--|--|--|
| 0.25" (6.35mm) | 0.375" (9.53mm) | 0.5" (12.7mm) | 0.75" (19.05mm) | 1" (25.4mm) | 1.25" (31.75mm) | | | |
| 1.50" (38.1mm) | 1.75" (44.45mm) | 2" (50.8mm) | 2.25" (57.15mm) | 2.50" (63.5mm) | 2.75" (69.85mm) | | | |
| 3" (76.2mm) | 3.25" (82.55mm) | 3.50" (88.9mm) | 3.75" (95.25mm) | 4" (101.6mm) | | | | |
| Compression Sheets: 48"W x 96"L (122cm x 244cm) | | | | | | | | |
| 0.25" (6.35mm) | 0.375" (9.53mm) | 0.5" (12.7mm) | 0.75" (19.05mm) | 1" (25.4mm) | 1.25" (31.75mm) | | | |
| 1.50" (38.1mm) | 1.75" (44.45mm) | 2" (50.8mm) | 2.25" (57.15mm) | 2.50" (63.5mm) | 2.75" (69.85mm) | | | |
| 3" (76.2mm) | 3.25" (82.55mm) | 3.50" (88.9mm) | 3.75" (95.25mm) | 4" (101.6mm) | | | | |
| Compression Sheets: 48"W x 120"L (122cm x 305cm) | | | | | | | | |
| 0.25" (6.35mm) | 0.375" (9.53mm) | 0.5" (12.7mm) | 0.75" (19.05mm) | 1" (25.4mm) | 1.25" (31.75mm) | | | |
| 1.50" (38.1mm) | 1.75" (44.45mm) | 2" (50.8mm) | 2.25" (57.15mm) | 2.50" (63.5mm) | 2.75" (69.85mm) | | | |
| 3" (76.2mm) | 3.25" (82.55mm) | 3.50" (88.9mm) | 3.75" (95.25mm) | 4" (101.6mm) | | | | |
| Compression Sheets: 60"W x 120"L (152cm x 305cm) | | | | | | | | |
| 0.25" (6.35mm) | 0.375" (9.53mm) | 0.5" (12.7mm) | 0.75" (19.05mm) | 1" (25.4mm) | 1.25" (31.75mm) | | | |
| 1.50" (38.1mm) | 1.75" (44.45mm) | 2" (50.8mm) | 2.25" (57.15mm) | 2.50" (63.5mm) | 2.75" (69.85mm) | | | |
| 3" (76.2mm) | 3.25" (82.55mm) | 3.50" (88.9mm) | 3.75" (95.25mm) | 4" (101.6mm) | | | | |
| | | | | | | | | |

LAST REVISED: 08/18/2025

This information is offered solely for your consideration, examination and verification, and is to be construed neither as a warranty nor guarantee that the same results as those stated herein will be obtained by the use to which others may put the material. Each user of the material should make his own tests to determine the characteristics and suitability of the material for his own particular use and the use which will be made of the completed product. This publication is not to be taken as a license to operate under, or a recommendation to infringe any patients. The observance of all legal regulations and patents is the responsibility of the user. The buyer's exclusive remedy against the seller shall be for the repair or replacement of defective stock. No other remedy (including, but not limited to, incidental or consequential damages for lost profits, lost sales, injury to person or property, or other incidental or consequential loss) shall be available to the buyer.

EXCLUSION OF WARRANTIES: THERE ARE NO WARRANTIES AS TO THE MATERIAL DESCRIBED HEREIN, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR PARTICULAR PURPOSE. ANY VALUES STATED IN SELLER'S ITERATURE ARE TYPICAL PROPERTIES ONLY.