



P: 1.800.999.1700 | F: 610.459.1084 | info@westlakeplastics.com | 490 West Lenni Road, Lenni, PA 19052 U.S.A.

Propylux HS®



Propylux® HS (Heat Stabilized polypropylene) extruded shapes are made from FDA, USP VI compliant polypropylene resin. Its broad chemical resistance, low moisture absorption, hydrolysis resistance, and toughness make it ideal for medical and life science applications. It is put through a unique heat stabilization process that stress-relieves the material, improves the dimensional stability, and enables the material to be repeatedly steam sterilized without loss of mechanical properties, aesthetics or dimensional stability. Suitable sterilization methods include steam autoclaving, EtO gas, and cold sterilization. Propylux® HS is fully lot traceable.

INDUSTRY



COLORS AVAILABLE

Aqua	Black	Brown	Dark Blue	Dark Green	Grey
Light Blue	Magenta	Natural	Neon Green	Orange	Purple
Red	Rust	White	Yellow		

ATTRIBUTES

- Steam Sterilizable ✓

- Biocompatibility ✓

- Dimensional Stability ✓

- Chemical Resistance ✓

SHAPES

- Extruded Slab ✓

- Extruded Rod ✓



P: 1.800.999.1700 | F: 610.459.1084 | info@westlakeplastics.com | 490 West Lenni Road, Lenni, PA 19052 U.S.A.

Propylux HS®

TYPICAL PROPERTIES

PROPERTY	TEST STANDARD	ENGLISH UNITS	METRIC UNITS
Mechanical			
Flexural Modulus	D790	313 kpsi	2,158.00 MPa
Flexural Strength - 5%	D790	9.2 kpsi	64.00 MPa
Izod Impact Resistance - Notched	D256	0.90 ft-lb/in	48.00 J/m
Tensile Elongation @ Break	D638	20-60%	20-60%
Tensile Elongation @ Yield	D638	4.60 %	4.60 %
Tensile Strength @ Break	D638	3.9 kpsi	27.00 MPa
Tensile Strength @ Yield	D638	5 kpsi	35.00 MPa
Thermal			
HDT @ 66 psi	D648	302 °F	150 °C
HDT @ 264 psi	D648	160 °F	71 °C
Physical			
Specific Gravity	D792	0.90	0.90

*Data above is based on testing of machined test specimens made from extruded bar stock



P: 1.800.999.1700 | F: 610.459.1084 | info@westlakeplastics.com | 490 West Lenni Road, Lenni, PA 19052 U.S.A.

Propylux HS®

PRODUCT SHAPES & DIMENSIONS

Rods: 48"L (122cm)

2.25" (57.15mm)	2.50" (63.5mm)	2.75" (69.85mm)	3" (76.2mm)	3.25" (82.55mm)	3.50" (88.9mm)
-----------------	----------------	-----------------	-------------	-----------------	----------------

Rods: 96"L (244cm)

0.5" (12.7mm)	1" (25.4mm)	1.25" (31.75mm)	1.50" (38.1mm)	1.75" (44.45mm)	2" (50.8mm)
---------------	-------------	-----------------	----------------	-----------------	-------------

Extruded Slabs: 24"W (61cm)

0.5" (12.7mm)	0.75" (19.05mm)	1" (25.4mm)	1.25" (31.75mm)	1.50" (38.1mm)	1.75" (44.45mm)
2" (50.8mm)	2.25" (57.15mm)	2.50" (63.5mm)	2.75" (69.85mm)		

LAST REVISED: 02/06/2025

This information is offered solely for your consideration, examination and verification, and is to be construed neither as a warranty nor guarantee that the same results as those stated herein will be obtained by the use to which others may put the material. Each user of the material should make his own tests to determine the characteristics and suitability of the material for his own particular use and the use which will be made of the completed product. This publication is not to be taken as a license to operate under, or a recommendation to infringe any patents. The observance of all legal regulations and patents is the responsibility of the user. The buyer's exclusive remedy against the seller shall be for the repair or replacement of defective stock. No other remedy (including, but not limited to, incidental or consequential damages for lost profits, lost sales, injury to person or property, or other incidental or consequential loss) shall be available to the buyer.

EXCLUSION OF WARRANTIES: THERE ARE NO WARRANTIES AS TO THE MATERIAL DESCRIBED HEREIN, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR PARTICULAR PURPOSE. ANY VALUES STATED IN SELLER'S LITERATURE ARE TYPICAL PROPERTIES ONLY.