





P: 1.800.999.1700 | F: 610.459.1084 | info@westlakeplastics.com | 490 West Lenni Road, Lenni, PA 19052 U.S.A.

# **Tempalux®**



Tempalux® Polyetherimide (PEI) is made from resin that is suitable for use in certain food contact applications, contact your local Westlake Plastics representative for specific regulatory declarations. Tempalux is an amorphous material that offers a combination of useful characteristics, including high dielectric strength, high strength at elevated temperatures (up to 180°C for extended periods of time), high modulus, and broad chemical resistance. Tempalux® is inherently flame resistant with low smoke emission. The material has good resistance to environmental stress cracking when exposed to a wide variety of chemicals.

#### INDUSTRY





Semiconductor and


## COLORS AVAILABLE





## ATTRIBUTES

Defense



#### SHAPES

Extruded Slab	
Extruded Sheet	<b>⊘</b>
Extruded Film	<b>⊘</b>
Extruded Rod	<b>⊘</b>







P: 1.800.999.1700 | F: 610.459.1084 | info@westlakeplastics.com | 490 West Lenni Road, Lenni, PA 19052 U.S.A.

# **Tempalux®**

## TYPICAL PROPERTIES

PROPERTY	TEST STANDARD	ENGLISH UNITS	METRIC UNITS			
Mechanical						
Flexural Modulus	D790	497 kpsi	3,430 MPa			
Flexural Strength - Yield	D790	25 kpsi	173 MPa			
Izod Impact Resistance - Notched	D256	0.99 ft-lb/in	53 J/m			
Tensile Elongation @ Break	D638	60.00 %	60.00 %			
Tensile Elongation @ Yield	D638	7.00 %	7.00 %			
Tensile Modulus	D638	519 kpsi	3,580 MPa			
Tensile Strength @ Break	D638	13 kpsi	90 MPa			
Tensile Strength @ Yield	D638	15 kpsi	110 MPa			
Thermal						
HDT @ 264 psi	D648	393 °F	201 °C			
Physical						
Moisture Absorption	D570	0.25 %	0.25 %			
Specific Gravity	D792	1.27	1.27			
Electrical						
Volume Resistivity	D257	1 x 10 <sup>17</sup> ohm-cm	1 x 10 <sup>17</sup> ohm-cm			

<sup>\*</sup>Data above is based on testing of injection molded test specimens







P: 1.800.999.1700 | F: 610.459.1084 | info@westlakeplastics.com | 490 West Lenni Road, Lenni, PA 19052 U.S.A.

# **Tempalux®**

PRODUCT SHAPES & DIMENSIONS

Rods: 48"L (122cm)							
2.25" (57.15mm)	2.5" (63.5mm)	2.75" (69.85mm)	3" (76.2mm)	3.25" (82.55mm)	3.5" (88.9mm)		
3.75" (95.25mm)	4" (101.6mm)	4.25" (107.95mm)	4.50" (114.3mm)	4.75" (120.65mm)			
Rods: 96"L (244cm)							
0.5" (12.7mm)	0.75" (19.05mm)	1" (25.4mm)	1.25" (31.75mm)	1.5" (38.1mm)	1.75" (44.45mm)		
2" (50.8mm)							
Extruded Slabs: 24"W (61cm)							
0.5" (12.7mm)	0.75" (19.05mm)	1" (25.4mm)	1.25" (31.75mm)	1.5" (38.1mm)	1.75" (44.45mm)		
2" (50.8mm)							
Extruded Sheets: 48"W x 96"L (122cm x 244cm)							
0.03" (0.76mm)	0.035" (0.89mm)	0.06" (1.52mm)	0.062" (1.57mm)	0.08" (2.03mm)	0.09" (2.29mm)		
0.095" (2.41mm)	0.125" (3.18mm)	0.1875" (4.76mm)	0.25" (6.35mm)				
Extruded Films: 26"W (66cm)							
0.002" (0.05mm)	0.003" (0.08mm)	0.004" (0.1mm)	0.005" (0.13mm)	0.01" (0.25mm)	0.02" (0.51mm)		

# LAST REVISED: 01/30/2025

This information is offered solely for your consideration, examination and verification, and is to be construed neither as a warranty nor guarantee that the same results as those stated herein will be obtained by the use to which others may put the material. Each user of the material should make his own tests to determine the characteristics and suitability of the material for his own particular use and the use which will be made of the completed product. This publication is not to be taken as a license to operate under, or a recommendation to infringe any patents. The observance of all legal regulations and patents is the responsibility of the user. The buyer's exclusive remedy against the seller shall be for the repair or replacement of defective stock. No other remedy (including, but not limited to, incidental or consequential damages for lost profits, lost sales, injury to person or property, or other incidental or consequential loss) shall be available to the buyer.

EXCLUSION OF WARRANTIES: THERE ARE NO WARRANTIES AS TO THE MATERIAL DESCRIBED HEREIN, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR PARTICULAR PURPOSE. ANY VALUES STATED IN SELLER'S ITERATURE ARE TYPICAL PROPERTIES ONLY.