



P: 1.800.999.1700 | F: 610.459.1084 | info@westlakeplastics.com | 490 West Lenni Road, Lenni, PA 19052 U.S.A.

Zelux® W



Zelux® W is a window grade polycarbonate (PC) that is optically clear with excellent dimensional stability, good strength, and stiffness, offering service temperatures up to 250°F. Zelux® W is often used for structural applications when clarity and impact strength are essential, including: lenses, manifolds, sight glass, and machine guards.


INDUSTRY



Aerospace



Engineering











Semiconductor and ESD

COLORS AVAILABLE



Transparent

ATTRIBUTES

 Transparent	
 Dimensional Stability	
 Impact Resistance	
 Optical Clarity	

SHAPES

Compression Sheet	
-------------------	---



P: 1.800.999.1700 | F: 610.459.1084 | info@westlakeplastics.com | 490 West Lenni Road, Lenni, PA 19052 U.S.A.

Zelux® W

TYPICAL PROPERTIES

PROPERTY	TEST STANDARD	ENGLISH UNITS	METRIC UNITS
Mechanical			
Flexural Modulus	D790	339 kpsi	2,344 MPa
Flexural Strength - 5%	D790	13.6 kpsi	93 MPa
Izod Impact Resistance - Notched	D256	17 ft-lb/in	907 J/m
Tensile Elongation @ Break	D638	170 %	170 %
Tensile Elongation @ Yield	D638	6 %	6 %
Tensile Modulus	D638	350 kpsi	2,413 MPa
Tensile Strength @ Break	D638	10.4 kpsi	71 MPa
Tensile Strength @ Yield	D638	8.8 kpsi	60 MPa
Thermal			
HDT @ 264 psi	D648	264°F	129°C
Physical			
Moisture Absorption	D570	0.15 %	0.15 %
Specific Gravity	D792	1.20	1.20
Electrical			
Volume Resistivity	D257	1 x 10 ¹⁷ ohm-cm	1 x 10 ¹⁷ ohm-cm

*Data above is based on testing of injection molded test specimens



P: 1.800.999.1700 | F: 610.459.1084 | info@westlakeplastics.com | 490 West Lenni Road, Lenni, PA 19052 U.S.A.

Zelux® W

PRODUCT SHAPES & DIMENSIONS

Compression Sheets: 48"W x 96"L (122cm x 244cm)

0.375" (9.53mm)	0.5" (12.7mm)	0.75" (19.05mm)	1" (25.4mm)	1.25" (31.75mm)	1.5" (38.1mm)
1.75" (44.45mm)	2" (50.8mm)	2.25" (57.15mm)	2.5" (63.5mm)		

LAST REVISED: 01/05/2024

This information is offered solely for your consideration, examination and verification, and is to be construed neither as a warranty nor guarantee that the same results as those stated herein will be obtained by the use to which others may put the material. Each user of the material should make his own tests to determine the characteristics and suitability of the material for his own particular use and the use which will be made of the completed product. This publication is not to be taken as a license to operate under, or a recommendation to infringe any patents. The observance of all legal regulations and patents is the responsibility of the user. The buyer's exclusive remedy against the seller shall be for the repair or replacement of defective stock. No other remedy (including, but not limited to, incidental or consequential damages for lost profits, lost sales, injury to person or property, or other incidental or consequential loss) shall be available to the buyer.

EXCLUSION OF WARRANTIES: THERE ARE NO WARRANTIES AS TO THE MATERIAL DESCRIBED HEREIN, EITHER EXPRESSED OR IMPLIED, INCLUDING, BUT NOT LIMITED TO, ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR PARTICULAR PURPOSE. ANY VALUES STATED IN SELLER'S LITERATURE ARE TYPICAL PROPERTIES ONLY.